

ABSTRACT OF THE DISCLOSURE

High aspect ratio openings can be etched in silicon having straight walls and rounded bottoms using as an etch gas a mixture including SF_6 , HBr and O_2 in a plasma chamber wherein the chamber is connected to an RF power source and the substrate is mounted on a support connected to a bias power source.

5

09882441-061501
"T4T28860"